



Timberix™



Perforated

E 16/16/8



Trademark and 2026 ©

Timberix™ Perforated panel is made with a 2-layer perforation structure, which traps and diffracts sound in the holes. The sound that passes through the perforation is further absorbed by an acoustic substrate such as fibreglass or mineral wool, which reduces reverberation in the room.



Technical Specifications

Structure	Core, Surface Finish, Backing
Core	E1 MDF, FR MDF, Black MDF, MgO
Surface Finish	Melamine, PVC, Veneer, Paint
Standard Dimension	600mm x 600mm, 600mm x 1200mm, 1200mm x 2400mm
Standard Thickness	15mm
Distances Between Two Holes	16/16mm
Diameter Of Holes	8mm
Standard Pattern	16/16/8mm (E)
Open Area	19.63%
Edge Banding	None, PVC, ABS
Formaldehyde Emission	EN 13986 = E1
Fire Classification	EN 13501-1 = Class B s1, d0 ASTM E84-23 = Class A
Acoustic Test Configuration	Perforated E 16/16/8 with Insulation
Weighted Absorption (aw)	ISO 11654 = 0.80 (L), Class B
Noise Reduction Coefficient (NRC)	ASTM C423 = 0.95